

# Deb's Glazing Application Process



## The Foot

Write "deb" on the bottom with AMACO underglaze pencil (black)  
 Apply 3 red dots under text with AMACO Velvet Underglaze (Red V-382)  
 Was foot Ring with Reed Wax - purchased through <http://www.clayartcenter.net/>  
 (Let wax dry overnight)  
 Paint Nan's Base with colorant over name/dots  
 Wipe off drips of glaze off of wax  
 Wax over the painted on glaze covering the center of foot  
 (Let wax dry overnight)



## The Interior

Pour Nan's Clear (with or without colorant) into the interior, quickly swirl and pour out.  
 Wax over the interior glaze with Reed Wax  
 (Let wax dry overnight)

## The Details

Paint bright color swatches of Wright's Water Blue  
 Wax over Swatches  
 (Let wax dry overnight)  
 Apply dots/speckles of underglaze - using AMACO Velvets and applicator bottle



## The Main Dip or Base Layer

Dip or pour each piece in a bucket of glaze. If it is too big to dip - spray the first layer of glaze.  
 Wipe off foot ring and larger interior drips of glaze while they are wet and easy to remove

## Sprayed Layers

Arrange multiple pieces on a ware board.  
 Arrange foam masks on the inside of the pots  
 Spray with 2-3 different glazes to create variation in the surface  
 Wipe off all the overspray carefully

**Firing** Fire pottery to Cone 6 in an electric kiln

<b>Nan's Clear</b> <i>(Interior Liner Glaze)</i>	<b>Wright's Water Blue</b> <i>(Chartreuse Swatch)</i>	<b>Heino</b> <i>(Base/ Main Exterior Glaze)</i>	<b>Dragon</b> <i>(Sprayed in Uneven Layers)</i>
Ferro Frit 3195 7.63 Gerstley Borate 14.04 Custer Feldspar 15.3 EPK 16.87 Whiting 16.87 Silica 28.5 Strontium 1.11  Bentonite 2%  ~ <i>Light Buttercup Colorants</i> Cerdec-Degussa Stain #239416 Yellow 3% & Cerdec-Degussa Stain #239616 Orange 1%  ~ <i>Light Chartreuse</i> Mason Stain #6236 3%	Lithium 3 Strontium 9 Ferro Frit 3110 59 EPK 12 Silica 17  Bentonite 2%  ~ <i>Chartreuse Variation</i> Chrome Oxide 0.25%	Custer Feldspar 30 Nepheline Syenite 20 Silica 5 Whiting 17 Kaolin 14 Gerstley Borate 5 Zinc 9  Bentonite 2%  ~ <i>Coral Variation</i> Mason Stain #6032 - 4%	Minspar 44 Cornwall Stone 22 Whiting 18 EPK 5 Zinc 7  Bentonite 2%  ~ <i>Black (not for food surface)</i> Copper Carbonate 3% Manganese Dioxide 4% Cobalt Carbonate 0.25%  ~ <i>Blue Variation</i> Cobalt Carbonate 0.5%

